



*The Plastic Films Specialist*

## GS41 Technical Data Sheet

### **Description and Applications**

Tenopex®PC GS41 is an extruded polycarbonate film, which is one side velvet textured and the other side gloss. It offers great dimensional stability, which is typically used for applications needing forming, die-cutting and embossing processes. It also provides excellent printability, and can be printed with screen print using traditional solvent based inks, wax based inks, and Indigo inks.

### **Typical Property Values**

Property	Test Method	Units	Value
<b>Physical</b>			
Density	ASTM D792	g/cm <sup>3</sup>	1.2
Water Absorption , 24hrs	ASTM D570	%	0.35
<b>Optical</b>			
Light Transmission	ASTM D1003	%	89-91
Haze	ASTM D1003	%	40
<b>Mechanical</b>			
Tensile Strength	ASTM D882	MPa	≥60
Tensile Elongation at Break	ASTM D882	%	100-150
Young Modulus	ASTM D882	MPa	≥2100
Impact Strength (0.76mm)	ISO 6603-1	J	31
<b>Thermal</b>			
Heat Deflection Temperature at 1.82Mpa	ASTM D648	°C	135
Coefficient of Thermal Expansion	ASTM D696	10 <sup>-5</sup> /°C	7
Coefficient of Thermal Exchange	ASTM C177	W/m.°C	0.19
Shrinkage at 150°C	ASTM D1204	%	1.4



*The Plastic Films Specialist*

## GS41 Technical Data Sheet

### Electrical

Dielectric Strength	ASTM D149	V	17000
Surface Resistivity	ASTM D257	$\Omega$ /square	$10^{15}$
Volume Resistivity	ASTM D257	$\Omega$ .cm	$10^{16}$

### UL Flammability

Film thickness $\leq$ 0.25mm	UL94	VTM-2
Film thickness $\geq$ 0.375mm	UL94	V-2

### Manufacturing Gauge Specifications

Nominal Gauge Ranges	Min/Max Tolerances of Nominal
0.175mm	+/- 10%
0.25mm - 0.375mm	+/- 7%
0.5mm	+/- 5%

These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local sales representative. Reported values are based on 0.250 mm thickness film unless otherwise noted.

Each user is responsible for making its own determination as to the suitability of Tenopex's products, services and recommendations for the user's particular use through appropriate end-use testing and analysis. Although any information or technical recommendation will be given without warranty nor guarantee nor implied, that the results indicated herein are obtained under end-use conditions. Except as provided in seller's standard conditions of sale, seller shall not be responsible for any loss resulting from any uses of its products or services described herein.